



DUNBAR – FK150

2:1 SHRINK RATIO, FLEXIBLE, HEAT SHRINKABLE POLYVINYLIDENE FLUORIDE (PVDF) TUBING

Applications

DUNBAR-FK150 is a flexible, thin wall, flame retardant, heat shrinkable polyvinylidene fluoride (PVDF) tube. It is designed for applications requiring outstanding abrasion and cut-through resistance. It reliably protects wires, solder joints, terminals, connections, and components from most industrial fuels, solvents and chemicals.

Features

- ★ Shrink ratio: 50% or more in the radial direction
+5%, -10% or less in the axial direction
- ★ Continuous operating temperature: -55°C (-67°F) to 150°C (302°C)
- ★ Thin wall
- ★ High resistance to fuel, chemicals and oils

Standard

- ★ SAE AS23053/18 Class 2 (Formerly AMS-DTL-23053/18 Class 2)
- ★ UL 224: VW-1, 600V, 150°C (File Number: E319303)
- ★ RoHS & REACH Compliant

Specification Values

Property		Test Method	Value	
Physical	Unaged	Tensile strength	ASTM D638	Min. 2500 psi
		Elongation		Min. 300%
	Aged	Elongation	225°C/168 hrs	Min. 250%
	Fluid Resistance	Tensile strength	24°C/24 hrs 6 Fluids	Min. 2000 psi
		Elongation		Min. 250%
	Concentricity		ASTM D2671	Min. 70%
	Heat shock		275°C/4 hrs	No cracking, flowing or dripping
	Low Temp. Flexibility		-55°C/4 hrs	No cracking
	Specific Gravity		ASTM D792	Max. 2.00
Secant Modulus		ASTM D882	25,000 ~ 100,000 psi	
Electrical	Dielectric strength		ASTM D2671	Min. 400 volts/mil
	Volume resistivity		ASTM D876	Min. 10 ¹¹ Ω - cm
Chemical	Copper corrosion		160°C/16 hrs	No corrosion
	Fungus Resistance		ASTM G21	No growth
	Water Absorption		ASTM D570	Max. 0.5%
	Flammability		ASTM D2671	Pass

Rev. June 2018




Dunbar Products, LLC
Tubing and Identification Products

1302 Champion Circle, Carrollton, Texas 75006
Tel: (469) 568-0800
Fax: (469) 568-0808



DUNBAR – FK150

2:1 SHRINK RATIO, FLEXIBLE, HEAT SHRINKABLE POLYVINYLIDENE FLUORIDE (PVDF) TUBING



Product Dimensions

Minimum Shrink Temperature: 125°C

Size	Expanded		Recovered				Standard Spool Length
	Internal Diameter (Minimum) (D)		Internal Diameter (Maximum) (d)		Minimum Wall Thickness (t)		
Inch Size	In.	mm	In.	mm	In.	mm	Ft.
3/64"	0.046	1.2	0.023	0.6	0.008	0.2	500
1/16"	0.063	1.6	0.031	0.8	0.008	0.2	500
3/32"	0.093	2.4	0.046	1.2	0.008	0.2	500
1/8"	0.125	3.2	0.062	1.6	0.008	0.2	500
3/16"	0.187	4.7	0.093	2.4	0.008	0.2	250
1/4"	0.250	6.4	0.125	3.2	0.009	0.2	250
3/8"	0.375	9.5	0.187	4.7	0.009	0.2	200
1/2"	0.500	12.7	0.250	6.4	0.009	0.2	200
3/4"	0.750	19.1	0.375	9.5	0.014	0.3	100
1"	1.000	25.4	0.500	12.7	0.016	0.4	100

Standard Color: Clear & Black
 Optional Color(s): Available, please inquire

Rev. June 2018



Dunbar Products, LLC
 Tubing and Identification Products

1302 Champion Circle, Carrollton, TX 75006
 Tel: (469) 568-0800
 Fax: (469) 568-0808